

++++
 +++ Post's Cone 1 White #1 +++
 +++

This glaze comes from John Post at <http://www.johnpost.us>

Date: 12/01/99

EPK	1500	15 %
Frit 3195	2000	20 %
Flint	500	5 %
Frit 3124	6000	60 %
	-----	-----
	10000	100 %
Superpax	1500	15 %

Notes:

Amaco lowfire glazes brushed over the top of this glaze work well and don't run off even at cone 1. This glaze looks best over a terracotta body.

=====
 Chemical Analysis
 =====

Na2O	0.30	Al2O3	0.51	SiO2	3.63
K2O	0.02	B2O3	0.67	ZrO2	0.30
CaO	0.68				

Alumina:Silica ratio is 1.00 : 7.11
 Neutral:Acid ratio is 1.00 : 3.33
 Alkali:Neutral:Acid ratio is 1.00 : 1.18 : 3.93

Expansion coefficient: 71.4 x 10e-7 per degree C

